

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶: D21H 27/10 // 11:18, 17:34, 15:10	A1	(11) International Publication Number: WO 99/00549 (43) International Publication Date: 7 January 1999 (07.01.99)
(21) International Application Number: PCT/US98/13429 (22) International Filing Date: 29 June 1998 (29.06.98) (30) Priority Data: 60/051,241 30 June 1997 (30.06.97) US 09/080,759 18 May 1998 (18.05.98) US (71) Applicant: KIMBERLY-CLARK WORLDWIDE, INC. [US/US]; 401 North Lake Street, Neenah, WI 54957 (US). (72) Inventors: KAPIK, Rene; 5 Nichole Court, Cheshire, CT 06410 (US). DEKA, Ganesh, C.; 10550 Stonepoint Place, Duluth, GA 30097 (US). (74) Agents: JONES, Neil, C. et al.; Dority & Manning, P.A., P.O. Box 1449, Greenville, SC 29602-1449 (US).	(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE, GH, GM, GW, HU, ID, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, UZ, VN, YU, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i>	
(54) Title: MEDICAL PACKAGING PAPER (57) Abstract A medical packaging substrate formed from a cellulosic pulp and/or synthetic fibers and a binder material is provided by the present invention. The substrate is usable to form medical packages for surgical instruments, medical devices, and medical appliances. The fabric is gas-pervious so that gas sterilization techniques may be used to sterilize the contents of any package made from the material. The substrate is manufactured using a latex deposition process wherein the binder material is applied prior to or during formation of the web. <div style="text-align: center; margin-top: 200px;">ds 11, 12</div>		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

MEDICAL PACKAGING PAPER

The present invention is based on provisional patent application Serial No. 60/051,241 filed June 30, 1997, and priority is hereby claimed therefrom.

Field of the Invention

The present invention relates generally to fabrics useful in forming packages for the medical field, including packaging for medical instruments that require a sterilization process. More specifically, the present invention relates to an improved medical packaging substrate produced by combining wood pulp, synthetic fibers, latex, and various optional physical property-enhancing add-ons. The latex is applied to the fibers by a latex deposition process.

Background of the Invention

Surgical instruments and devices and appliances must be sterilized prior to use. Such instruments and devices are often wrapped in a hospital surgical supply or central supply room prior to being sterilized. Typically, the packages, in which the instruments and devices are placed are made of a textile or nonwoven fabric which serves to protect the instruments during sterilization and to preserve their sterility upon subsequent storage until the packages are opened and the instruments used. Fabrics typically used in this area are either tightly woven textiles or nonwovens which possess a closed structure with certain porosity characteristics. (As used herein, the term "fabric" is intended to encompass any sheet-like or web material which is formed, in whole or in part, from a plurality of fibers.) The resulting packages usually take the form of bags, pouches, or the like.

The normal sterilization procedure used by hospitals and surgical supply rooms today involves using sterilizing materials, such as steam or ethylene oxide gas, to penetrate porous packages in

which the surgical instruments or medical devices are maintained.

The gas flows through the pores in the packaging material and sterilizes the instruments contained therein. Over time, the gas will diffuse out of the package. Other sterilization processes well known
5 in the art have also been used to sterilize surgical instruments and medical devices.

Thus, a suitable fabric for packaging surgical instruments and medical devices must exhibit the combined effects of good permeability to steam, ethylene oxide, or Freon sterilizing gases while
10 offering adequate bacterial filtration efficiency in order to prevent the entry of bacteria into the package. In addition to being permeable, the fabric should be strong and exhibit relatively high internal bonding, or delamination and tear resistances. The product should also possess a certain degree of fluid repellency to prevent further
15 transmission of the bacteria. Other properties necessary for such packaging is that it be non-toxic in accordance with industry and federal guidelines, substantially lint-free, odor-free, and drapable.

In terms of permeability, a fabric's suitability as a bacteria barrier may be partially predicted by a cumulative pore number of at
20 least 3 million pores per square centimeter. The cumulative pore number reflects the creation of surfaces that prohibit the passage of bacteria by enabling the bacteria to lodge on a surface and, thus, be trapped by the barrier. The greater the cumulative pore numbers, the greater possibility of bacteria lodging in a pore and not passing
25 through the substrate.

Other desirable properties for suitable bacteria barrier fabrics include those normally desired in other fabrics for use in forming packages and coverings, including strength, particularly in terms of delamination and tear resistance, suppleness, drapability,
30 smoothness, etc. Obviously, the inclusion of such characteristics will

depend on the particular product for which the bacteria barrier fabric is to be used.

One example of these gas-pervious, bacteria-impervious materials which has certain of these properties is a spunbonded polyolefin material sold under the trademark TYVEK® by E.I. DuPont De Nemours & Co. TYVEK® is a lightly consolidated or unconsolidated fabric made from spun bonded sheets of flash-spun polyolefin (usually polyethylene or polypropylene) plexifilamentary film-fibril strands. The general procedure for manufacturing TYVEK® is disclosed in U.S. Patent No. 3,169,898 to Steuber.

TYVEK® fabric exhibits high strength, as well as providing the necessary pore distribution to allow for sterilization processes to act on instruments contained within packaging made from the material. TYVEK® material acts as a barrier to particulate matter that is sub-micron in size. TYVEK®, however, is a purely synthetic material and lacks the qualities inherent in material made with cellulosic webs. Such characteristics include suppleness, softness, drapability, and ease of printing.

To form sterile packaging trays from bacteria barrier fabrics, a surgical device or medical appliance is placed in an impervious tray or tub and a layer of the gas-pervious, bacterial-impervious paper or plastic is sealed to flanged edges of the tray. The sealed package is then exposed to ethylene oxide which permeates the paper or plastic and sterilizes the contents of the package. Since the paper or plastic is designed to prevent the passage of bacteria, the contents of the package will remain sterile until the seal is broken. One such example of a needle/suture package is disclosed in U.S. Patent No. 4,183,431 to Schmidt et al. Another package for housing a medical instrument is shown in U.S. Patent No. 5,031,775 to Kane.

A high-strength porous material, such as TYVEK®, may also be used as the backing material for a medical packaging breather

pouch. Such pouches generally have an outer layer of plastic film material heat sealed to the edges of a TYVEK® sheet to secure the medical instrument within the package. One such breather pouch is described in U.S. Patent No. 5,217,772 to Brown et al.

5 U.S. Patent No. 5,418,022 to Anderson et al. relates to a method of forming a pocket from a spunbonded olefin sheet and a microbial resistant package produced thereby. The package disclosed therein comprises a spunbonded olefin sheet material, such as TYVEK®, at least a portion of which has been stretched or
10 thermally deformed.

Alternatives to DuPont's TYVEK® product have also been developed. In particular, medical packaging substrates consisting of paper-based webs that have been saturated with binders such as latex have also been used for packaging surgical instruments and
15 medical devices. In some of these substrates, a synthetic staple fiber, such as polyester or nylon, is incorporated directly into the wood pulp furnish for forming the composite web. Latex, usually at a high add-on, is necessary in order to bind the synthetic fibers to the cellulose-based web because, otherwise, the fibers would tend to
20 pick or pull out of the sheet with relative ease.

The synthetic fiber that is incorporated into the product increases the tear resistance of the medical packaging substrate but generally reduces delamination resistance and tensile strength. The add-on latex builds up the necessary delamination resistance to
25 prevent the substrate from splitting during its end use.

The latex in these bacteria barrier products is normally applied by a saturation process which typically involves dipping the formed fabric web into a bath of latex or subjecting the fabric web to latex-saturated rollers. Alternatively, the webs are subjected to latex
30 application while still on the forming web through the use of various emulsion processes and the like. In each of these previously known

processes for forming bacteria barrier fabrics, the latex is applied to the fabric after the web has been formed and dried or after the web has been formed on the wire. Such processes where latex is applied to a formed web are generally referred to herein as "latex saturation" processes. The application of latex in this manner fills in many of the smaller (less than 1 micron) pores in the fabric, often reducing the permeability of the fabric.

Examples of such products include products designated as BP 388 and BP 321 which are available from Kimberly-Clark Corporation. These products are base papers that are typically used as medical packaging substrates and comprise various amounts of cellulosic pulps and synthetic latex. Although such products function well as medical packaging substrates, their permeability characteristics and tear, puncture, and delamination resistances could be improved.

U.S. Patent No. 5,204,165 to Schortmann discloses a nonwoven laminate having barrier properties which is described as being suitable for industrial, hospital, and other protective or covering uses. The laminate consists of at least one thermoplastic fiber layer bonded with a wet-laid fabric layer made from a uniform distribution of cellulose fibers, polymeric fibers, and a binder. In one embodiment, spunbond polyester fiber layers are ultrasonically bonded on each side of a wet-laid barrier fabric made of eucalyptus fibers and polyester fibers. The barrier fabric is bonded with an acrylic latex binder. The binder is added to the formed polymeric/cellulosic web after the web is formed. The binder may be added by any one of several methods, including foamed emulsion, gravure roll polymer emulsion, spraying, padding and nip-pressure binder pick-up. Schortmann is an example of a barrier fabric formed using a latex saturation process.

Another process for saturating a formed web with a latex binder is disclosed in U.S. Patent No. 5,595,828 to Weber. A

polymer-reinforced paper, which includes eucalyptus fibers, is disclosed. After forming the web from eucalyptus fibers and, optionally, other fibers such as non-eucalyptus cellulosic fibers and/or synthetic fibers, the web is saturated with a latex binder. Again, this particular latex-saturated fabric would be more suitable for use as a bacteria barrier if more of the pores remained open as opposed to being filled with binder material.

Although various processes are known for making papers using a latex deposition process wherein a binder material is precipitated onto the forming fibers prior to forming the paper sheet, such resulting products have not heretofore been generally used as forms of sterilizable medical packaging substrates. For example, U.S. Patent No. 5,466,336 to Kinsley, Jr. describes a process for making a paper-based product comprising a paper sheet, an aqueous latex binder and a release agent. The product is made by preparing a slurry of cellulosic and/or synthetic pulp and a polymeric latex binder and then depositing the latex polymer particles onto the surface of the cellulosic fibers and adding an emulsion of lecithin and a fatty acid or fatty acid derivative. Coagulation of the latex into particles once in the slurry is promoted by agents such as alum or by altering the pH of the slurry. There is no indication, however, in Kinsley, Jr. that the resulting paper otherwise meets the requirements of a bacteria barrier fabric or is suitable for such use.

U.S. Patent No. 4,178,205 to Wessling et al. also discloses a process for forming a high strength non-woven fibrous material prepared by mixing an aqueous slurry of negatively charged fiber with a specific type of cationic latex and then forming a web from that slurry. The fibers used include both natural and synthetic fibers. Like Kinsley, Jr., there is no teaching that the resulting material meets the requirements of a bacteria barrier fabric.

U.S. Patent No. 4,510,019 to Bartelloni discloses a process for making paper by combining fibrous materials, a latex, and a bridging or cross-linking agent. The bridging or cross-linking agents, however, link or bridge the paper-making fibers to uncoagulated latex particles. In fact, the patent discloses that coagulation and precipitation of the latex is to be minimized and preferably prevented.

Despite the availability of several alternative bacteria barrier fabrics, a need still exists for further improved medical substrates that can be used in forming the packages for housing and sterilizing medical devices and surgical instruments until they are used. Such packaging must allow for known sterilization materials to enter into the package and sterilize the enclosed appliances while at the same time exhibit high strength, at least in terms of delamination and tear resistance.

Summary of the Invention

It is an object of the present invention to provide an improved medical packaging substrate for housing surgical instruments, medical devices, medical appliances, and the like.

Another object of the present invention is to provide a substrate for use in medical packaging which provides the necessary tear, puncture, and delamination resistances while maintaining the ability to allow passage of sterilization gases therethrough.

It is a further object of the present invention to provide a barrier product sufficient to protect a medical device stored within the barrier product from bacterial contamination.

A further object of the present invention is to provide a process for producing a bacteria barrier fabric which results in a high strength fabric that exhibits suitable porosity characteristics sufficient for use as a medical packaging substrate.

Another object of the present invention is to provide a process which utilizes a latex deposition process to form a medical packaging substrate.

5 These and other objects are achieved by generally providing a medical packaging substrate constructed from wood pulp fibers and/or synthetic fibers, a binder material, and various strength-producing and water-resisting chemicals. More specifically, the present invention involves the formation of a medical packaging bacteria barrier fabric using a latex deposition process whereby a
10 binder material, such as latex, is applied to a fabric web during or prior to formation of the web.

The use of the latex deposition process in forming the fabric, overcomes the problems encountered with latex saturation processes. The binder material is added to the web-forming slurry
15 along with one or more deposition aids. The deposition aids promote coagulation and particle formation of the binder material so that the binder particles may attach to the fibers used in forming the web. The binder particles will attach themselves to the fibers when they contact the fibers.

20 When the web is then subsequently formed, the binder material does not substantially interfere with the pore structure of the web as it does when a latex saturation process is used to add the strengthening binder material to the web. Instead, the deposited binder material enhances delamination and tear resistance of the web
25 by binding the fibers together without clogging the pores necessary for maintaining a suitable fabric permeability.

Other objects, features and aspects of the present invention are discussed in greater detail below.

Detailed Description of Preferred Embodiment

30 It is to be understood by one of ordinary skill in the art that the present discussion is a description of exemplary embodiments only

and is not intended as limiting the broader aspects of the present invention, which broader aspects are embodied in the exemplary construction.

Generally speaking, the present invention is a medical packaging substrate constructed from wood pulp fibers and/or synthetic fibers, a binder material, and various strength-producing and water-resisting chemicals. The substrate is produced using a latex deposition process instead of the widely used latex saturation process.

More specifically, the present invention involves the formation of a medical packaging bacteria barrier fabric using a latex deposition process whereby a binder material, such as latex, is applied to a fabric web during or prior to formation of the web. The binder material is added to the web-forming slurry along with one or more deposition aids. The deposition aids promote coagulation and particle formation of the binder material so that the binder particles may attach to the fibers used in forming the web. The binder particles will attach themselves to the fibers when they contact the fibers.

The web may be formed from cellulosic pulp fibers alone, synthetic fibers alone, or a mixture of cellulosic pulp and synthetic fibers. When used, the cellulosic pulp fiber component of the furnish for making the bacteria barrier web may include various woody and/or non-woody cellulosic fiber pulps. Pulp includes fibers from natural sources such as woody and non-woody plants. Woody plants include, for example, deciduous and coniferous trees. Non-woody plants include, for example, cotton, flax, esparto grass, milkweed, straw, jute hemp, and bagasse.

The pulp may be a mixture of different types and/or qualities of pulp fibers. For example, the invention may include a pulp containing more than about 50 percent by weight, low-average fiber length pulp

and less than about 50 percent by weight, high-average fiber length pulp (e.g., virgin softwood pulp). The low-average fiber length pulp may be characterized as having an average fiber length of less than about 1.2 mm. For example, the low-average fiber length pulp may have a fiber length from about 0.7 mm to about 1.2 mm. The high-average fiber length pulp may be characterized as having an average fiber length of greater than about 1.5 mm. For example, the high-average fiber length pulp may have an average fiber length from about 1.5 mm to about 6 mm. The fiber mixture may contain about 75 percent, by weight, low-average fiber length pulp and about 25 percent, by weight, high-average fiber length pulp.

The low-average fiber length pulp may be certain grades of virgin hardwood pulp and secondary (i.e., recycled) fiber pulp from sources such as, for example, newsprint, reclaimed paperboard, and office waste. The high-average fiber length pulp may be bleached and/or unbleached virgin softwood pulps.

In accordance with the present invention, any of the various wood and nonwood pulps and other cellulosic fibers may be incorporated into the pulp furnish. Illustrative examples of suitable lignocellulosic pulps include southern pines, northern softwood kraft pulps, red cedar, hemlock, black spruce and mixtures thereof. Exemplary high-average fiber length wood pulps include those available from the Kimberly-Clark Corporation under the trade designations Longlac 19 and Coosa River 55.

Other various cellulosic fibers that may be used in the present invention include eucalyptus fibers, such as Aracruz Eucalyptus, and other hardwood pulp fibers available under the trade designations Coosa River 57, Longlac 16 and Quinuesco. Obviously, other cellulosic fibers may be utilized in the present invention, depending on the particular characteristic desired in the bacteria barrier.

In one particular embodiment of the present invention, a pulp mixture utilizing a eucalyptus pulp and a high average fiber length pulp is utilized. In particular, a 75% by weight amount of Aracruz Eucalyptus and a 25% by weight amount of Longlac 19 are combined into the pulp mixture for formation of the bacteria barrier web in this embodiment.

Refinement of the pulp is necessary in order to obtain a web possessing the properties necessary to use the web as a bacteria barrier. In particular, refinement of the pulp is carried out by beating or otherwise agitating the cellulosic material until the material is sufficiently separated into relatively individual pulp fibers. Such refinement may be carried out by any number of various known methods such as in commercial grade pulp beaters. Such refining processes are within the known skill in the art.

The more highly refined pulps result in more effective bacteria barriers. This is because the use of individualized pulp fibers will form a web having many circuitous and tortuous pore channels. Obviously, the more tortuous a pore channel path is, the less likely bacteria will be able to navigate the channel and permeate through the web. As indicated above, suitability as a bacteria barrier fabric can generally be determined by cumulative pore number, with 3 million per square centimeter being acceptable for such products. In addition, webs having a log reduction value (LRV) of two or above are generally suitable as bacteria barriers. The higher the estimated LRV, the greater the bacteria barrier properties. For example, an LRV change from 1 to 2 indicates a ten times improvement in the barrier. Although lower LRVs are acceptable, producers of medical packagings generally find substrates having an LRV of 3 or higher to be especially suitable.

When processing a chosen pulp to be used in the present fabric, the amount of refinement is determined by the desired

cumulative pore number and other barrier properties. The following Table indicates how various refinement parameters affect pore size, cumulative pore size, and estimated LRVs in webs formed from the listed pulps. The pulps listed were subjected to a refinement beater known as a PFI Mill, available from Lorentzen and Wettre, at the indicated revolutions. Tensile strength is shown in kg/15 mm. Canadian Standard Freeness (CSF) is shown in milliliters and basis weight (B.W.) in grams per square meter. Thickness or caliper is shown in millimeters and the density is shown in grams per cubic centimeter. The pore size is indicated in microns, with a maximum and a minimum and a mean flow pore size (MFP). MFP indicates the pore size at a 50% air throughput level. The estimated LRVs are shown in Table 1.

TABLE 1

Pulp	Revolutions (PFI mill)	Tensile Sum	CSF ml	B.W. (g/m ²)	Caliper (mm)	Density (g/cc)	Porosity sec/1stht	Pore Size, Microns			Cumulative Pore No.	Est. LRV
								Max.	Min.	MFP		
Aracruz	250	0.20	622	56.6	0.1397	0.405	0.5	17.7	6.8	9.9	8.44×10^5	1.6
	1000	0.42	595	55.0	0.1295	0.425	0.6	17.7	6.0	9.1	1.01×10^6	1.8
	4000	0.56	578	53.3	0.1118	0.477	0.9	14.3	6.0	8.3	1.29×10^6	1.8
	6000	0.82	359	56.8	0.0940	0.604	5.2	8.6	2.1	3.3	4.85×10^6	2.8
	8000	0.89	302	56.9	0.0965	0.590	10.5	5.6	1.4	2.5	9.14×10^6	3.3
	10,000	1.02	196	39.7	0.0635	0.625	28.0	5.1	1.4	1.8	1.01×10^7	3.4
	13,000	1.14	148	43.8	0.0686	0.639	82.0	2.8	0.8	1.3	1.31×10^7	3.6
	250	0.21	758	56.3	0.1702	0.331	0.2	>300	13.8	30.2	8.21×10^4	0.0
Leaf River 90	1000	0.44	740	65.0	0.1549	0.420	0.3	54.6	10.3	19.0	2.60×10^5	0.7
	4000	0.69	680	60.3	0.1219	0.495	0.9	72.1	8.0	13.8	2.86×10^5	0.8
	6000	0.92	526	56.3	0.1067	0.528	3.1	56.4	2.9	6.4	1.07×10^6	1.8
	8000	0.85	463	54.5	0.0991	0.551	4.2	50.0	2.1	5.4	2.49×10^6	2.4
	10,000	0.94	353	60.9	0.0991	0.615	50.0	12.3	1.4	2.5	3.84×10^6	2.7

TABLE 1 (cont.)

Pulp	Revolutions (PFI mill)	Tensile Sum	CSF ml	B.W. (g/m ²)	Caliper (mm)	Density (g/cc)	Porosity sec/1sht	Pore Size, Microns			Cumulative Pore No.	Est. LRV
								Max.	Min.	MFP		
LL-16	100	0.30	675	61.1	0.1219	0.501	0.9	19.3	5.6	8.7	9.74 x 10 ⁵	1.7
	250	0.35	663	57.3	0.1194	0.480	0.9	23.3	6.2	9.0	1.00 x 10 ⁶	1.7
	500	0.49	637	54.7	0.1219	0.449	1.1	16.1	5.2	7.9	1.38 x 10 ⁶	1.8
	1000	0.56	617	57.8	0.1041	0.555	2.2	16.1	5.0	7.3	7.47 x 10 ⁵	1.6
	2000	0.65	562	48.0	0.0813	0.591	3.6	20.5	3.0	5.0	1.70 x 10 ⁶	2.1
	4000	0.99	414	51.6	0.0864	0.597	20.0	8.3	1.6	2.3	3.28 x 10 ⁶	2.6
Hamac K-10	100	0.19	700	55.9	0.1549	0.361	2.1	23.3	4.9	7.7	1.32 x 10 ⁶	1.8
	250	0.29	740	54.9	0.1321	0.416	1.7	21.4	5.2	8.1	8.29 x 10 ⁵	1.6
	500	0.43	670	57.8	0.1219	0.474	2.5	22.3	4.1	7.2	9.69 x 10 ⁵	1.6
	1000	0.56	670	54.3	0.1168	0.465	4.5	15.6	2.5	4.9	2.31 x 10 ⁶	2.3
	4000	0.87	552	55.0	0.0914	0.601	11.0	12.3	1.4	2.5	3.86 x 10 ⁶	2.7
	5000	1.03	518	49.9	0.0914	0.546	24.6	13.9	1.8	3.2	2.68 x 10 ⁶	2.4
LL-19	8000	1.24	414	49.1	0.0787	0.624	14.6	16.1	1.8	2.9	2.46 x 10 ⁶	2.4

The furnish may also include, or be made from 100% of, synthetic fibers such as rayon fibers, polyvinyl alcohol fibers, ethylene vinyl alcohol copolymer fibers, and various polyolefin fibers. Suitable polymeric fibers for use in the present invention include fibers made from polyolefins, polyesters, polyamides, and copolymers and blends thereof. Polyolefins suitable for the fibers include polyethylene, e.g., high density polyethylene, medium density polyethylene, low density polyethylene and linear low density polyethylene; polypropylene, e.g., isotactic polypropylene, syndiotactic polypropylene, blends thereof, and blends of isotactic polypropylene and atactic polypropylene; polybutylene, e.g., poly(1-butene) and poly(2-butene); polypentene, e.g., poly(1-pentene) and poly(2-pentene); poly(3-methyl-1-pentene); poly(4-methyl-1-pentene); and copolymers and blends thereof. Suitable copolymers include random and block copolymers prepared from two or more different unsaturated olefin monomers, such as ethylene/propylene and ethylene/butylene copolymers. Polyamides suitable for the fibers include nylon 6, nylon 6/6, nylon 4/6, nylon 11, nylon 12, nylon 6/10, nylon 6/12, nylon 12/12, copolymers of caprolactam and alkaline oxide diamine, and the like, as well as blends and copolymers thereof. Suitable polyesters include polyethylene terephthalate, polybutylene terephthalate, polytetramethylene terephthalate, polycyclohexylene-1,4-dimethylene terephthalate, and isophthalate copolymers thereof, as well as blends thereof. Of these suitable polymers, more desirable polymers are polyolefins, most desirably polyethylene and polypropylene, because of their commercial availability and importance, as well as their chemical and mechanical properties.

In addition, bicomponent fibers may be utilized in addition to the cellulosic fibers and unitary synthetic fibers and are, in some embodiments, preferred. Bicomponent fibers are multicomponent fibers wherein two fibers having differing characteristics are combined

into a single fiber. Bicomponent fibers generally have a core and sheath structure where the core is a polyester and the sheath is a polyolefin. Other bicomponent fiber structures, however, may also be utilized. For example, bicomponent fibers may be formed with the two components residing in various side-by-side relationships as well as concentric and eccentric core and sheath configurations.

When used, bicomponent fibers aid in increasing the strength of the web. The outer sheath of the bicomponent fiber should be capable of adhering to cellulosic fibers so that the structure of the web is reinforced through their use. One particular example of a suitable bicomponent fiber is sold under the name "Celbond T255" by Hoechst Celanese. Celbond T255 is a synthetic polyester/polyethylene bicomponent fiber which is capable of adhering to cellulosic fibers when its outer sheath is melted at a temperature of approximately 128°C.

Various binder materials may be used in the present inventive process. Any of the latex binders commonly employed for reinforcing paper can be utilized and are well known to those having ordinary skill in the art. Suitable binders include, by way of illustration only, polyacrylates, including polymethacrylates, poly(acrylic acid), poly(methacrylic acid), and copolymers of the various acrylate and methacrylate esters and the free acids; styrene-butadiene copolymers; ethylene-vinyl acetate copolymers; nitrile rubbers or acrylonitrile-butadiene copolymers; poly(vinyl chloride); poly(vinyl acetate); ethylene-acrylate copolymers; vinyl acetate-acrylate copolymers; neoprene rubbers or trans-1,4-polychloroprenes; cis-1,4-polyisoprenes; butadiene rubbers or cis- and trans-1,4-polybutadienes; and ethylene-propylene copolymers.

Specific examples of commercially available latex binders are set forth as examples in Table 2 below:

TABLE 2

Suitable Latexes for Deposition	
Polymer Type	Product Identification
Polyacrylates	Hycar® 26083, 26084, 26120, 26104, 26106, 26322, 26469 B. F. Goodrich Company Cleveland, Ohio Rhoplex® HA-8, HA-12, HA-16 NW-1715, B-15 Rohm and Haas Company Philadelphia, Pennsylvania Carboset® XL-52 B. F. Goodrich Company Cleveland, Ohio
Styrene-butadiene copolymers	Butofan® 4264, 4262 BASF Corporation Sarnia, Ontario, Canada DL-219, DL-283, DL-239 Dow Chemical Company Midland, Michigan
Nitrile rubbers	Hycar® 1572, 1577, 1570X55, 1562X28 B. F. Goodrich Company Cleveland, Ohio
Poly(vinyl chloride)	Vycar® 352, 552 B. F. Goodrich Company Cleveland, Ohio
Ethylene-acrylate copolymers	Michem® Prime 4990 Michelman, Inc. Cincinnati, Ohio Adcote 56220 Morton Thiokol, Inc. Chicago, Illinois
Vinyl acetate-acrylate copolymers	Xlink 2833 National Starch & Chemical Co. Bridgewater, New Jersey

In making the web of the present invention, a pulp furnish is formed according to normal procedures. The furnish may consist of only cellulosic pulp fibers, only synthetic fibers, or a mixture of cellulosic pulp fibers and synthetic fibers. A binder material, such as one or more of the above-described latex materials, is added to the furnish so that the binder material is "deposited" onto the fibers. Various deposition aids may be added to the furnish to assist in coagulation of the binder material into particles and in attaching the binder material particulates to the fibers.

Deposition of the binder material onto the fibers while in the furnish in this invention is in contrast to the latex saturation process previously used to create bacteria barriers. During such latex saturation processes, binder materials are applied to the web after it is formed. In the present deposition process, the binder material adheres to the fibers as small "adhesive-like" balls or particles before the paper is formed and dried. This process allows the pores to remain relatively unobstructed whereas latex saturation processes tend to close a number of the smaller pores by forming a film on the web. The latex saturation processes result in a less than perfect bacteria barrier substrate.

Among the various deposition aids which may be used include Alum, Kymene 736, Nalco 7607, Parex 631NC, and Kymene 557LX.

The web is made from the furnish according to known papermaking processes.

Various other additives may also be used in the bacteria barrier-making process. For example, sizing agents to impart water resistance, wet-strength agents to improve delamination resistance, and other agents may be added either to the furnish or to the formed web. One such exemplary sizing agent is Aquapel 752 and one such exemplary wet-strength agent is Parex 631NC. Other agents, include, by way of example only, starches and dry-strength resins

which also enhance the physical properties of the web by increasing the delamination resistance of the final product. One such exemplary starch is a cationic potato starch sold under the designation Astro X-200 and one such exemplary dry-strength resin is Accostrength 85.

5 Cross-linking agents and/or hydrating agents may also be added to the pulp furnish.

Optionally, the fabric formed from the present process may be calendered by known processes using steel calendering rolls. Calendering will add smoothness to the fabric. Processes such as
10 "supercalendering," which uses a harder steel roll and a softer, polishing, roll, can also be used. In supercalendering, a high-gloss polish is created.

If so desired, the fabric so made may be treated with a separate bacteria barrier. One such exemplary bacteria barrier
15 technique is provided by Rexam via their MICROMOD® process. This process involves subjecting the fabric to a technique which fills any large pores with particulates which act as a bacteria barrier. In addition, anti-microbial agents may be added to the pore-embedded particular matter so that anti-microbial activity will be exhibited by the
20 fabric. Obviously, such techniques are not required if sufficiently refined pulp is used in making the web because the bacteria barrier properties relative to pore size and number will already be inherent in the product.

The fabric is then supplied to a maker of medical packaging
25 which then transforms the fabric into the appropriate packaging necessary for storing medical devices and appliances and surgical instrumentation.

In order to make comparative tests to commercially available products used in medical packaging, the inventive substrate was
30 made according to the following examples.

EXAMPLE 1

An Aracruz Eucalyptus virgin pulp in an amount of 75% by weight and a Longlac 19 virgin pulp were refined in a Valley beater to approximately 350 to 450 ml CSF. Commercial acrylic latex (Hycar 26796) was deposited onto the fibers at 15 to 20% bone dry weight of the fiber. Kymene 736, at 10 pounds per ton, and Nalco 7607, at 1 pound per ton, were used as deposition aids. The pulp was diluted to handsheet consistency. A neutral internal sizing agent (Aquapel 752) was added at 0.15 to 0.3% bone dry weight to impart water resistance to the web. Parex 631NC was added at 0.5 to 1.0% bone dry weight as wet-strength agent to improve delamination resistance of the web. The Aquapel and Parex additives were added at the handsheet mold instead of the size press because it was believed that saturation with these chemicals may have been detrimental to the bacteria barrier properties of the web. Celbond T255 (a synthetic polyester/polyethylene bicomponent fiber) was added to the handsheet mold at 5% bone dry weight to increase the delamination resistance of the web. The web was then wet pressed at about 600 psig for 5 minutes and dried on a steam-heated drum. The chemical additions of Aquapel and Parex were cured at 105°C for 4 minutes. The Celbond was melted at 180°C for 25 seconds. The formed sheets were steel calendered at 0 psig for 2 passes to a target Gurley porosity of 8 to 14 seconds per sheet. The target basis weight was 25 pounds per ream, conditioned.

25

EXAMPLE 2

The process of Example 1 was repeated in preparing another substrate except that Hycar 26410 was substituted for Hycar 26796 as the binder material and two additional wet-end additives were used to increase the delamination resistance of the sheet. Potato starch (Astro X-200) was applied at 20 pounds per ton and a dry-strength resin (Accostrength 85) was applied at 1% bone dry weight.

30

EXAMPLES 3-10

Additional handsheets were made for comparative purposes. Generally, the sheets were formed according to the process of Examples 1 and 2 except as follows. Example 3 was a control sheet with no latex application and no wet-strength additives. Example 4 utilized a latex saturation process wherein Hycar 26410 at 20 parts pick-up (ppu) was coated onto the formed web after drying. The additives for Examples 5 - 10 are indicated in Table 3 below. In Table 3, the basis weights (B.W.), caliper (in millimeters), density (in grams per cubic centimeter), porosity (in seconds per 100 cubic centimeters), tear strength (in grams), delamination strength (in grams per 15 mm), and the cumulative pore number (in exponential terms) are shown. The percentage reduction in cumulative pore number is relative to Example 3 which is the control sample with no latex addition.

In each of the Examples, the latex utilized was Hycar 26410 at 20 ppu (whether deposited or saturated); the wet strength agents were added at 1.0% bone dry weight; the basis weights are shown as conditioned weights; the pulp (75% Aracruz Eucalyptus/25% Longlac 19) used was refined to 420 milliliters CSF; wet pressing was performed at 500 psig; starch was added to the formed handsheet at 20 pounds per ton; talc was added at 6 pounds per ton and no polyvinyl alcohol fiber was used.

TABLE 3

Example	Latex Appl.	Wet Strength		Second Dep. Agent	B.W. #/R	Cal. mm	Dens. g/cc	Poros. sec	Tear g	Delam. g	Cumulative Pore No. (% red)
		Type	Appl.								
3	None	None	None	None	23.2	0.1422	0.6313	14	125	128	1.39×10^7
4	Saturate	None	None	None	22.0	0.129	0.6783	12	90	290	2.79×10^6 (-80%)
5	Deposit	None	None	Kymeme 557LX	23.8	0.1270	0.7045	14	100	341	1.14×10^7 (-18%)
6	Deposit	Kymeme 736	Saturate	Kymeme 557LX	24.1	0.1270	0.7133	14	99	347	7.42×10^6 (-47%)
7	Deposit	Parez 631NC	Saturate	Kymeme 557LX	23.9	0.1321	0.6802	11	94	341	5.26×10^6 (-62%)
8	Deposit	Parez 631NC	Wet-end	Kymeme 557LX	24.0	0.1321	0.6831	14	98	367	9.14×10^6 (-34%)
9	Deposit	Kymeme	Wet-end	Kymeme 557LX	23.7	0.1321	0.6745	11	104	321	9.03×10^6 (-35%)
10	Deposit	Parez	Wet-end	Nalco 7607	22.9	0.1270	0.6778	15	96	377	9.35×10^6 (-33%)

EXAMPLES 11-21

In the Examples summarized in Tables 4a and 4b below, the effects of the use of bicomponent fibers at the handsheet mold to form the bacteria barrier properties of various sheets made according to the process described in Example 1 are shown. As in Example 1, each of the sheets in Examples 11-20 comprise 75% eucalyptus and 25% softwood fibers. In Examples 11-16, no bicomponent fibers were added. In Examples 17-18, bicomponent fibers (Celbond T255) in an amount of 2.5% bone dry weight were utilized and in Examples 19-20, the same bicomponent fibers were added in an amount of 5.0% bone dry weight. Example 21 is BP388, which is a commercial base paper available from Kimberly-Clark and which has been used as a medical packaging component (or substrate) as described above. Obviously, Example 21 has not been prepared according to the present invention.

Table 4a reflects the percentage of wet strength agent (Kymene 557XL), percentage of Aquapel 752, whether the sheet was oven aged at 105°C for 4 minutes, the maximum and minimum pore sizes, the mean flow pore size, the cumulative pore number, the estimated LRV, the smoothness of the sheet in Sheffield units (s.u.) and the opacity (which is 100 times the ratio of light reflected by a paper specimen when the specimen is backed by a black body of 0.5% reflectance or less to that when the specimen is backed by a thick stack of the same type of paper specimens). In addition, Table 4b presents the basis weights, caliper, porosity, cobb size (indicative of the ability to repel water or prevent water from being absorbed) in grams of water at 5 minutes per 20 milliliters of water, porosity, wet tensile strength at 10 seconds, stretch percentage, tear strength and delamination strength.

TABLE 4a

Example	Wet Strength (%)	Aquapel (%)	Oven Aged?	Pore Size, microns			Cumulative Pore No.	Est. LRV	Smoothness (s.u.)	Opacity (%)
				Max	Min	MFP				
11	0	0	yes	7.5	1.4	2.7	1.26 x 10 ⁷	3.5	280	83.7
12	0	0.15	yes	10.2	1.9	3.3	8.21 x 10 ⁶	3.3	280	84.5
13	0	0.30	yes	7.5	1.6	2.7	1.09 x 10 ⁷	3.5	225	84.8
14	0	0.30	no	10.4	2.2	3.5	5.55 x 10 ⁶	3.0	260	83.8
15	0.5	0.30	yes	11.4	2.2	3.7	5.45 x 10 ⁶	3.0	300	84.9
16	0.5	0.30	no	13.7	2.7	4.5	3.26 x 10 ⁶	2.8	290	84.4
17	0	0.30	yes	15.8	2.4	4.5	4.14 x 10 ⁶	2.8	340	85.2
18	0.5	0.30	yes	14.0	2.5	4.5	3.74 x 10 ⁶	2.8	320	85.4
19	0	0.30	yes	13.5	2.8	3.8	6.27 x 10 ⁶	3.1	335	85.0
20	0.5	0.30	yes	11.2	1.9	3.6	6.08 x 10 ⁶	3.1	370	85.6
21 (BP388)	---	---	---	25.5	2.7	9.6	3.40 x 10 ⁵	0.9	240/220	84.0

TABLE 4b

Example	B.W. (#/R)	Caliper (mil)	Porosity (sec/1)	Cobb Size (g H2O)	Tensile (kg)	W. Tensile (kg)	Stretch (%)	Tear (g)	Delamin. (g)
11	23.8	5.7	15	1.6	7.8	0.5	4.6	108	320
12	24.4	5.6	8	0.7 (-55%)	7.7	0.6	3.9	108	310
13	24.1	5.6	13	0.3 (-81%)	7.6	0.6	4.4	109	305
14	23.8	5.7	8	0.4 (-78%)	6.7	0.5	3.6	110	285
15	25.3	6.0	7	0.3 (-81%)	8.5	1.0	4.5	107	320
16	24.6	6.1	6	0.3 (-81%)	7.5	0.9	3.6	114	285
17	25.8	6.6	5	0.3 (-81%)	7.8	1.3	3.9	130	340
18	24.5	6.2	6	0.3 (-81%)	8.7	1.6	4.3	121	355
19	24.4	6.3	7	0.3 (-81%)	8.0	1.5	4.8	124	340
20	26.5	6.6	7	0.3 (-81%)	8.9	2.1	5.3	129	395
21 (BP388)	22.6	4.4	6	0.22	8.6/5.8	1.9/1.9	2.9/8.5	60/6 5	370

In Examples 22 and 23, the wet pressing effects on LRV were measured. In these Examples, a sheet made according to the process of Example 1 were made with the characteristics shown below in Table 5. The effects of wet pressing at 400 psig and at 1000 psig are shown.

TABLE 5

Example	Wet Pressing (psig)	B.W. (#/R)	Caliper (mil)	Porosity (sec/1sht)	Delamin. (g)	Est. LRV
22	400	22.1	5.4	11	320	3.2
23	1000	23.3	5.1	16	350	3.8

The bacteria barrier of the present invention was then compared to previously known substrates that are typically used as bacteria barriers. The inventive substrate was prepared according to the process of Example 1 and then compared to the listed base
5 papers (BP designations) available from Kimberly-Clark and TYVEK® from DuPont. The results of those comparisons are listed in Table 6.

In Table 6, the basis weight, caliper, porosity, cumulative pore number, estimated LRV, Nelson Bacterial Filtration Efficiency (BFE) (determined at 3 M spores/cm³ at 28 l/m flow rate) and the actual
10 LRV's measured according to ASTM 2.6 (determined at 1 MM spores/cm³ at 2.8 l/min. flow rate).

TABLE 6

Description	B.W. (#/R)	Caliper (mil)	Porosity (sec/1sht)	Regression Model			Nelson BFE (%)	LRV (ASTM)
				Cumulative Pore No.	Estimated LRV			
BP 388	22.6	4.6	8	6.34 x 10 ⁵	1.3	82.8	1.33	
BP 394	24.6	5.6	39	1.65 x 10 ⁶	2.1	99.4	2.16	
Tyvek	---	8.0	18	7.15 x 10 ⁶	3.2	99.8	5.09	
Example 1	22.0	5.0	17	1.00 x 10 ⁷	3.4	99.8	3.04	

The following test methods were employed to determine various reported characteristics and properties. ASTM refers to the American Society for Testing and Materials.

Where applicable in the tables above, the porosity was determined pursuant to the Gurley Hill Porosity test according to ASTM D-726-84. The basis weight was determined by ASTM D-3776-85 and is reported in pounds per ream. Tear strengths are reported in grams and were performed in accordance with the Elmendorf Tear Test, ASTM D689. The tensile strength is reported in kilograms per 15 millimeters and was determined by application on an Instron machine according to ASTM D828. The percentage of stretch was determined by ASTM D828. The cumulative pore number is given in exponential terms as pores per square centimeters. Pore size was determined using a Coulter Porometer commercially available from Coulter Electronics, Ltd., Luton Beds, England. The sample to be analyzed was thoroughly wetted so that all accessible pores were completely filled with liquid. The wetted sample was then placed in the sample body of the filter holder assembly, secured with a locking ring and the pore size value was accorded. The values are reported in microns for the maximum, minimum and mean flow pore size distribution.

Where applicable in the examples above, delamination was determined according to the following procedure. First, sample strips of the substrate were cut to dimensions of 2-1/2 inches x 7-1/2 inches long grain (7-1/2 inch in the machine direction). Two strips were cut per sample. An electric hot plate having a six-inch wide solid steel top was then heated to 312° F (156° C) and a piece of steel plate (1-1/2 inch x 6 inches x 1-1/2 inches) with an insulated handle in the center (weight 2640 grams which was equal to .9692 psi) was placed on top of the hot plate and preheated to 312° F (156° C). A 1/8 inch strip of Ideal "black" paper delamination tape (1 inch wide) was

placed on each side of the sample to be tested, with one superimposed upon the other, in the long grain direction of the sample. The tape was not preheated. The sample was then pressed between the hot plate and the steel plate for 20 seconds at 312° F (156° C), leaving 1 inch of tape on each end unpressed. The samples were then cooled and trimmed to 15 mm wide, ensuring that each edge of the Ideal tape was equally trimmed. An Instron tensile tester model TM-M was then calibrated and set up with a cross head speed of 30 cm/min; a chart speed of 3 cm/min; and a full scale load of 2 kilograms. Delamination resistance was then determined using the Instron in an attempt to delaminate the sample substrate being tested. Delamination is expressed in the tables above in grams per 15 mm.

Although preferred embodiments of the invention have been described using specific terms, devices, and methods, such description is for illustrative purposes only. The words used are words of description rather than of limitation. It is to be understood that changes and variations may be made by those of ordinary skill in the art without departing from the spirit and scope of the present invention which is set forth in the following claims. In addition, it should be understood that aspects of the various embodiments may be interchanged, both in whole or in part.

WHAT IS CLAIMED IS:

1. A process for forming a bacteria barrier substrate, said process comprising the steps of:
 - a) forming a furnish comprising refined fibers suitable for forming a bacteria barrier substrate;
 - 5 b) adding a binder material to said furnish under conditions sufficient to allow the binder material to be deposited onto said fibers;
 - c) forming a web from said furnish;
 - d) drying said web so as to form a bacteria barrier substrate.
2. The process of claim 1, wherein said refined fibers have a Canadian Standard Freeness of between about 300 ml to about 450 ml.
3. The process of claim 1, wherein said binder material is a latex binder.
4. The process of claim 1, wherein said binder material is chosen from the group consisting of polyacrylates, including polymethacrylates, poly(acrylic acid), poly(methacrylic acid), and copolymers of the various acrylate and methacrylate esters and the free acids; styrene-butadiene copolymers; ethylene-vinyl acetate
5 copolymers; nitrile rubbers or acrylonitrile-butadiene copolymers; poly-vinyl chloride); poly(vinyl acetate); ethylene-acrylate copolymers; vinyl acetate-acrylate copolymers; neoprene rubbers or trans-1,4-polychloroprenes; cis-1,4-polyisoprenes; butadiene rubbers or cis-and trans-1,4-polybutadienes; and ethylene-propylene copolymers.
5. The process of claim 1, wherein said bacteria barrier substrate, after drying, has a cumulative pore number of at least 3 million pores per square centimeter.
6. The process of claim 1, wherein said refined fibers comprise secondary fibers.

7. The process of claim 1, wherein said bacteria barrier substrate, after drying, exhibits a log reduction value of at least 2.
8. The process of claim 1, wherein said bacteria barrier substrate, after drying, exhibits a log reduction value of at least 3.
9. The process of claim 1, wherein further comprising the step of adding synthetic fibers to said furnish.
10. The process of claim 9, wherein said synthetic fibers comprise bicomponent fibers.
11. The process of claim 1, further comprising the step of calendaring said bacteria barrier substrate.
12. The process of claim 1, wherein said bacteria barrier substrate is treated with a separate bacteria barrier to further enhance the bacteria barrier properties of said substrate.
13. The process of claim 1, wherein said refined fibers comprise eucalyptus fibers.
14. The process of claim 1, further comprising the step of adding deposition aids to said furnish.
15. The process of claim 14, wherein said deposition aids are chosen from the group consisting of alum, KYMENE 736, NALCO 7607, KYMENE 557LX, and Parex 631NC.
16. The process of claim 1, further comprising the step of adding sizing agents to said furnish.
17. The process of claim 16, wherein said sizing agent is AQUAPEL 752.
18. The process of claim 1, further comprising the step of adding wet-strength agents to said furnish.
19. The process of claim 18, wherein said wet-strength agent is PAREZ 631NC.
20. The process of claim 1, further comprising the step of adding starches to said furnish.

21. The process of claim 20, wherein said starch is a cationic potato starch.
22. The process of claim 21, wherein said cationic potato starch is ASTRO X-200.
23. The process of claim 1, further comprising the step of adding dry-strength resins to said furnish.
24. The process of claim 23, wherein said dry-strength resin is ACCOSTRENGTH 85.
25. A bacteria barrier substrate having a cumulative pore number of at least 3 million pores per square centimeter, said substrate comprising refined pulp fibers and a binder material.
26. The bacteria barrier substrate of claim 25, further comprising synthetic fibers.
27. The bacterial barrier substrate of claim 26, wherein said synthetic fibers comprise bicomponent fibers.

INTERNATIONAL SEARCH REPORT

Intern: 1 Application No
PCT/US 98/13429

A. CLASSIFICATION OF SUBJECT MATTER
IPC 6 D21H27/10 //D21H11:18, D21H17:34, D21H15:10

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 6 D21H

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 4 510 019 A (BARTELLONI RENE) 9 April 1985 cited in the application see column 13, line 63 - column 20, line 28 ---	1,3,4,6, 11,14, 16,20
X	US 5 466 336 A (KINSLEY JR HOMAN B) 14 November 1995 cited in the application see the whole document ---	1,3,4,9, 14
X	US 5 204 165 A (SCHORTMANN WALTER E) 20 April 1993 cited in the application see the whole document ---	25,26
-/--		

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents:

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"G" document member of the same patent family

Date of the actual completion of the international search

2 October 1998

Date of mailing of the international search report

15/10/1998

Name and mailing address of the ISA
European Patent Office, P.B. 5816 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl.
Fax: (+31-70) 340-3016

Authorized officer

Songy, O

INTERNATIONAL SEARCH REPORT

Intern: al Application No

PCT/US 98/13429

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 5 308 691 A (LIM HYUN S ET AL) 3 May 1994 see the whole document ---	25,26
A	US 5 595 828 A (WEBER ROBERT E ET AL) 21 January 1997 cited in the application ---	
A	US 3 604 426 A (ERICKSON RICHARD E) 14 September 1971 -----	

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 98/13429

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 4510019 A	09-04-1985	FR 2505896 A	19-11-1982
		FR 2519663 A	18-07-1983
		FR 2524828 A	14-10-1983
		BR 8202072 A	22-03-1983
		CA 1183660 A	12-03-1985
		EP 0067076 A	15-12-1982
		JP 57199896 A	07-12-1982
		US 4445972 A	01-05-1984
		FI 822082 A,B,	09-07-1983
		AU 552651 B	12-06-1986
		CA 1195053 A	15-10-1985
		EP 0091529 A	19-10-1983
		FI 822500 A,B,	10-10-1983
		JP 58183753 A	27-10-1983
		ZA 8205838 A	27-07-1983
US 5466336 A	14-11-1995	US 5328567 A	12-07-1994
		AU 7451294 A	28-02-1995
		EP 0717802 A	26-06-1996
		WO 9504856 A	16-02-1995
		ZA 9405875 A	10-03-1995
		AU 3616693 A	03-09-1993
		CA 2129734 A	11-08-1993
		EP 0738345 A	23-10-1996
		JP 7503765 T	20-04-1995
		WO 9316229 A	19-08-1993
		US 5498314 A	12-03-1996
		US 5800675 A	01-09-1998
US 5204165 A	20-04-1993	NONE	
US 5308691 A	03-05-1994	CA 2173327 A	13-04-1995
		DE 69402561 D	15-05-1997
		DE 69402561 T	25-09-1997
		EP 0722389 A	24-07-1996
		ES 2101579 T	01-07-1997
		JP 9503459 T	08-04-1997
		WO 9509728 A	13-04-1995
US 5595828 A	21-01-1997	US 5622786 A	22-04-1997

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 98/13429

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 3604426 A	14-09-1971	NONE	